

APPLICANT:
STEELPRO COMPANY

4. Test Results :

TEST METHOD		Test item(s)	Requirement	P/F
		(S01)		
1	Abrasion resistance of glove[#] (NF EN 388:2004 §6.1) Lowest value of four tests : Performance Level :	290 1	---	---
2	Tear resistance of glove[#] (NF EN 388:2004 §6.3) Lowest value of four tests (N): Performance Level :	28 2	---	---

TEST METHOD		Test item(s)		Requirement	P/F	
		(S02)				
3	Blade cut resistance of glove[#] (NF EN 388:2004 §6.2) Sequence	Index (I)		---	---	
		Test 1	Test 2			
		1	1.9			2.1
		2	1.9			2.1
		3	1.9			2.0
		4	1.9			1.9
		5	1.9			1.9
Average (I):		1.9	2.0	---	---	
Lowest average value (I) :		1.9		---	---	
Performance Level :		1		---	---	

*** Table of Performance Level for Glove**

Test Item	Performance Level					
	0 ^{**}	1	2	3	4	5
Abrasion Resistance (NF EN 388:2004 §6.1) Number of cycles (minimum)	< 100	100	500	2000	8000	---
Blade Cut Resistance (NF EN 388:2004 §6.2) Index (I) (minimum)	< 1.2	1.2	2.5	5.0	10.0	20.0
Tear Resistance (NF EN 388:2004 §6.3) Force (N) (minimum)	< 10	10	25	50	75	---

^{**} Performance level 0 means the glove falls below the minimum performance level for the given individual hazard.

- End of report -