

APPLICANT:
STEELPRO COMPANY

4. Test Results :

TEST METHOD		Test item(s) (S01)	Requirement	P/F
1	Abrasion resistance of glove[#] (NF EN 388:2004 §6.1) Lowest value of four tests : Performance Level :	774 2	--- ---	--- ---
2	Tear resistance of glove[#] (NF EN 388:2004 §6.3) Lowest value of four tests (N): Performance Level :	65 3	--- ---	--- ---

TEST METHOD		Test item(s) (S02)		Requirement	P/F
		Index (I)			
		Test 1	Test 2		
3	Blade cut resistance of glove[#] (NF EN 388:2004 §6.2) Sequence				
	1	5.1	3.9	---	
	2	4.4	3.5	---	
	3	2.8	3.8	---	
	4	2.8	5.0	---	
	5	3.5	3.7	---	
	Average (I):	3.7	4.0	---	
	Lowest average value (I) :			---	---
	Performance Level :	2		---	---

[#] Table of Performance Level for Glove

Test Item	Performance Level					
	0 ^{**}	1	2	3	4	5
Abrasion Resistance (NF EN 388:2004 §6.1) Number of cycles (minimum)	< 100	100	500	2000	8000	---
Blade Cut Resistance (NF EN 388:2004 §6.2) Index (I) (minimum)	< 1.2	1.2	2.5	5.0	10.0	20.0
Tear Resistance (NF EN 388:2004 §6.3) Force (N) (minimum)	< 10	10	25	50	75	---

^{**} Performance level 0 means the glove falls below the minimum performance level for the given individual hazard.

- End of report -